POLYESLINE

POLYESLINE S.L.

Polígono Industrial "Els Mollons". C/ Tapissers, 4 – 46970 Alaquas, Valencia –Spain. Tel: 0034 96 006 65 10 Mail: comercial@polyesline.com

Web site: www.polyesline.com

POLYES-FILM (B-21512)

TECHNICAL SPECIFICATION SHEET

ESCRIPTION: B-21512, Both side chemically treated, clear film having smooth surface, excellent clarity and good handling property.

APPLICATIONS: High clarity film suitable for high quality printing, lamination and other general application.

SALIENT FEATURES:

- High clarity and Transparency
- Excellent ink adhesion.
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

			TECHNICAL DATA				
Properties		Test method	Unit	B-21512			
PHYSICAL							
Thickness		ASTM D-374	Micron (Gauge)	50 (200)	75 (300)	100 (400)	
Yield		JPFTM	$m^2/kg (in^2/lb)$	14 (10000)	9.5 (6680)	7.1(4990)	
OPTICAL						•	
Haze		ASTM D-1003	%	1.5	1.5	1.6	
Total luminous transmittance		ASTM D-1003	%	90	90	90	
MECHANICAL							
Tensile strength (Min)	MD	ASTM D-882	Kg/cm ² (psi)	1800 (25600)	1700 (24200)	1700 (24200)	
	TD	ASTM D-882	Kg/cm ² (psi)	1800 (25600)	1700 (24200)	1700 (24200)	
Elongation (Min)	MD	ASTM D-882	%	100	120	120	
	TD	ASTM D-882	%	100	100	100	
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.50	0.50	0.50	
	Dy	ASTM D-1894	-	0.40	0.40	0.40	
THERMAL							
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5	2.5	
	TD	ASTM D-1204	%	0.4	1.5	1.5	
SURFACE							
Wetting tension (Min)		ASTM D-2578	Dyne / cm	40	40	40	
Electrical						•	
Volume Resistivity		ASTM D-256	Ohm cm	10^16	10^16	10^16	

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. POLYESFILM S.L. suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

POLYESLINE

POLYESLINE S.L.

Polígono Industrial "Els Mollons". C/ Tapissers, 4 – 46970 Alaquas, Valencia –Spain. Tel: 0034 96 006 65 10 Mail: comercial@polyesline.com

Web site: www.polyesline.com

POLYES-FILM (B-21512)

TECHNICAL SPECIFICATION SHEET

DESCRIPTION: B-21512, Both side chemically treated, clear film having smooth surface, excellent clarity and good handling property.

APPLICATIONS: High clarity film suitable for high quality printing, lamination and other general application. **SALIENT FEATURES:**

- High clarity and Transparency
- Excellent adhesion to solvent base ink.
- · High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

			TECHNICAL DATA					
Properties		Test method	Unit	B-21512				
PHYSICAL								
Thickness		ASTM D-374	Micron (Gauge)	125 (500)	175 (700)	250 (1000)		
Yield		JPFTM	$m^2/kg (in^2/lb)$	5.7 (4000)	4.1 (2880)	2.9 (2040)		
OPTICAL								
Haze		ASTM D-1003	%	1.8	2.4	3.0		
Total luminous transmittance		ASTM D-1003	%	90	90	90		
MECHANICAL						•		
Tensile strength (Min)	MD	ASTM D-882	Kg/cm ² (psi)	1700 (24200)	1700 (24200)	1600 (22800)		
	TD	ASTM D-882	Kg/cm ² (psi)	1700 (24200)	1700 (24200)	1600 (22800)		
Elongation (Min)	MD	ASTM D-882	%	120	120	120		
	TD	ASTM D-882	%	100	100	100		
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.50	0.50	0.50		
	Dy	ASTM D-1894	-	0.40	0.40	0.40		
THERMAL								
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5	2.5		
	TD	ASTM D-1204	%	1.5	1.5	1.5		
SURFACE								
Wetting tension (Min)		ASTM D-2578	Dyne / cm	40	40	40		
Electrical								
Volume Resistivity		ASTM D-256	Ohm cm	10^16	10^16	10^16		

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. POLYESFILM S.L. suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.