# POLYESLINE

#### **POLYESLINE S.L.**

Polígono Industrial "Els Mollons". C/ Tapissers, 4 – 46970 Alaquas, Valencia –Spain. Tel: 0034 96 006 65 10 Mail: comercial@polyesline.com

Web site: www.polyesline.com

POLYES-FILM (B-21611)

### TECHNICAL SPECIFICATION SHEET

**DESCRIPTION:** B-21611 is white opaque, one side chemically coated, other side plain film having smooth surface, excellent superior gloss, high opacity and good handling property.

**APPLICATIONS:** Film suitable for Label printing, Photographic printing, coating and other general application. **SALIENT FEATURES:** 

- High Opacity
- Excellent adhesion to solvent baseink
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

			TECHNICAL DATA				
Properties		Test method	Unit	B-21611			
PHYSICAL		•					
Thickness		ASTM D-374	Micron (Gauge)	50 (200)	75 (300)	125 (500)	
Yield		JPFTM	$m^2/kg (in^2/lb)$	14 (9850)	9.4 (6600)	5.6 (3950)	
OPTICAL		•					
Opacity (f	⁄lin)	CIE Standard	%	90	93	96	
Total luminous transmittance		ASTM D-1003	%	20	15	10	
MECHANICAL							
Tensile strength (Min)	MD	ASTM D-882	Kg/cm <sup>2</sup> (psi)	1400 (19900)	1400 (19900)	1400 (19900)	
	TD	ASTM D-882	Kg/cm <sup>2</sup> (psi)	1500 (21300)	1500 (21300)	1500 (21300)	
Elongation (Min)	MD	ASTM D-882	%	100	100	100	
	TD	ASTM D-882	%	80	80	80	
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.35	0.35	0.35	
	Dy	ASTM D-1894	-	0.30	0.30	0.30	
THERMAL		•					
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5	2.5	
	TD	ASTM D-1204	%	1.5	1.5	1.5	
SURFACE							
Wetting tension (Min)		ASTM D-2578	Dyne / cm	40	40	40	
Electrical							
Volume Resistivity		ASTM D-256	Ohm cm	10^16	10^16	10^16	

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. POLYESLINE S.L. suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

# POLYESLINE

#### **POLYESLINE S.L.**

Polígono Industrial "Els Mollons". C/ Tapissers, 4 – 46970 Alaquas, Valencia –Spain. Tel: 0034 96 006 65 10 Mail: comercial@polyesline.com

Web site: www.polyesline.com

POLYES-FILM (B-21611)

### TECHNICAL SPECIFICATION SHEET

**DESCRIPTION:** B-21611 is white opaque, one side chemically coated, other side plain film having smooth surface, excellent superior gloss, high opacity and good handling property.

**APPLICATIONS:** Film suitable for Label printing, Photographic printing, coating and other general application. **SALIENT FEATURES:** 

- High Opacity
- Excellent adhesion to solvent base ink
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

				TECHNICAL DATA	A			
Properties		Test method	Unit	B-21611				
PHYSICAL		•						
Thickness		ASTM D-374	Micron (Gauge)	175 (700)	250 (1000)			
Yield		JPFTM	$m^2/kg (in^2/lb)$	4.0 (2800)	2.8 (2000)			
OPTICAL								
Opacity (N	⁄lin)	CIE Standard	%	98	99			
Total luminous transmittance		ASTM D-1003	%	7	3			
MECHANICAL								
Tensile strength (Min)	MD	ASTM D-882	Kg/cm <sup>2</sup> (psi)	1400 (19900)	1300 (18500)			
	TD	ASTM D-882	Kg/cm <sup>2</sup> (psi)	1500 (21300)	1400 (19900)			
Elongation (Min)	MD	ASTM D-882	%	100	100			
	TD	ASTM D-882	%	80	80			
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.35	0.35			
	Dy	ASTM D-1894	-	0.30	0.30			
THERMAL		•						
Shrinkage (Max (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5			
	TD	ASTM D-1204	%	1.5	1.5			
SURFACE								
Wetting tension (	Min)	ASTM D-2578	Dyne / cm	40	40			
Electrical								
Volume Resistivity		ASTM D-256	Ohm cm	10^16	10^16			

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. POLYESLINE S.L. suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.