

**POLYESLINE S.L.U.**

Polígono Industrial "Els Mollons". C/ Tapissers, 4 – 46970 Alaquas, Valencia –Spain.

Tel: 0034 96 006 65 10 Mail: comercial@polyesline.com

Web site: www.polyesline.com

POLYES-FILM (B-21481)

TECHNICAL SPECIFICATION SHEET

DESCRIPTION: B-21481 is co extruded tough milky white Polyester Film with one side antistatic coated film having excellent surface and good electrical property.

APPLICATIONS: Suitable for insulation in rotating electrical machine and other general application.

SALIENT FEATURES:

- Tough flexibility to prevent delamination.
- Good insulation property
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability.



TECHNICAL DATA						
Properties	Test method	Unit	B-21481			
PHYSICAL						
Thickness	ASTM D-374	Micron (Gauge)	125 (500)	190 (760)	225 (900)	
Yield	JPFTM	m ² /kg (in ² /lb)	5.7 (4000)	3.7 (2600)	3.2(2225)	
OPTICAL						
Haze	ASTM D-1003	%	70	80	85	
Total luminous transmittance	ASTM D-1003	%	75	71	68	
MECHANICAL						
Tensile strength (Min)	MD	ASTM D-882	Kg/cm ² (psi)	1700 (24200)	1700 (24200)	1700 (24200)
	TD	ASTM D-882	Kg/cm ² (psi)	1700 (24200)	1700 (24200)	1700 (24200)
Elongation (Min)	MD	ASTM D-882	%	120	120	120
	TD	ASTM D-882	%	100	100	100
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.35	0.35	0.35
	Dy	ASTM D-1894	-	0.30	0.30	0.30
THERMAL						
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5	2.5
	TD	ASTM D-1204	%	1.5	1.5	1.5
Electrical						
Break Down Voltage	ASTM D-149	KV	17	20	21	
Surface Resistivity coated side	ASTM D-256	Ohm cm	10 ^{^11}	10 ^{^11}	10 ^{^11}	

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. POLYESLINE S.L.U. suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.