

**POLYESLINE S.L.U.**

Polígono Industrial "Els Mollons". C/ Tapissers, 4 – 46970 Alaquas, Valencia –Spain.

Tel: 0034 96 006 65 10 Mail: comercial@polyesline.com

Web site: www.polyesline.com**POLYES-FILM (T-21516)****TECHNICAL SPECIFICATION SHEET****DESCRIPTION:** T-21516, Both side chemically treated, clear film having smooth surface, excellent clarity and good handling property**APPLICATIONS:** High clarity film suitable for face shield application.**SALIENT FEATURES:**

- High clarity and Transparency
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

**TECHNICAL DATA**

Properties	Test method	Unit	T-21516				
PHYSICAL							
Thickness	ASTM D-374	Micron (Gauge)	175 (700)	190 (760)	225 (900)	250 (1000)	
Yield	PFTM	m ² /kg (in ² /lb)	4.1 (2880)	3.8 (2650)	2.85 (2214)	2.9 (2040)	
OPTICAL							
Haze	ASTM D-1003	%	2.0	2.2	2.4	2.6	
Total luminous transmittance	ASTM D-1003	%	90	90	90	90	
MECHANICAL							
Tensile strength (Min)	MD	ASTM D-882	Kg/cm ² (psi)	1700 (24200)	1650 (23500)	1600 (22800)	1600 (22800)
	TD	ASTM D-882	Kg/cm ² (psi)	1700 (24200)	1650 (23500)	1600 (22800)	1600 (22800)
Elongation (Min)	MD	ASTM D-882	%	120	120	120	120
	TD	ASTM D-882	%	100	100	100	100
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.50	0.45	0.50	0.50
	Dy	ASTM D-1894	-	0.40	0.35	0.40	0.40
THERMAL							
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5	2.5	2.5
	TD	ASTM D-1204	%	1.5	1.5	1.5	1.5
SURFACE							
Wetting tension (Min)	ASTM D-2578	Dyne / cm	40	40	40	40	

PFTM: POLY ESFILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

The values given in the technical data sheets of our products are typical performance data and are believed to be accurate. These are given in good faith, but it is up to the client to verify the suitability for his own particular purpose. POLYESLINE S.L.U. suggests to the customer to confirm these values and the compatibility of the product before use. POLYESLINE S.L.U. does not offer any guarantee or accept any responsibility for the suitability of the product for a particular use. For this reason, POLYESLINE S.L.U. will only be liable in the event that the material is defective, and only after its manufacturer confirms and ratifies it; and will never be responsible for the damages caused by its use, nor will it be responsible for them, nor for cost of the transport for return or replacement, if applicable