

 POLYESLINE	POLYESLINE S.L. Polígono Industrial "Els Mollons". C/ Tapissers, 4 – 46970 Alaquas, Valencia –Spain. Tel: 0034 96 006 65 10 Mail: comercial@polyesline.com Web site: www.polyesline.com
POLYES-FILM (PVC 200 my)	TECHNICAL SPECIFICATION SHEET

Fórmula_Base / Formulation / Grundrezeptur FB00456

Color / Colour / Farbe

FC09992

Espesor / Thickness / Dicke

200 µm



Parámetro Parameter Parameter	Normativa Regulation Nomen	Método Methode Methode	Valores Values Werte	Unidades Units Einheiten
Tolerancia de Espesor Thicknesstolerance Dickentoleranz	EN 1849-2	Micrometer	200 +/- 5%	my
Resistencia a la Rotura Tensile stress at break Bruchspannung	EN ISO 527 - 3	70 mm/min	Longitudinal Longitudinal Langs >47 Transversal Transversal Quer >43	MPa
Alargamiento en la rotura Tensile strain at break Bruchdehnung	EN ISO 527 - 3	70 mm/min	Longitudinal Longitudinal Langs >80 Transversal Transversal Quer	%
Contracción Shrinkage Schrumpf	DIN 53377	10 min.; + 80 oc	< -5,0	%

The values given in the technical data sheets of our products are typical performance data and are believed to be accurate. These are given in good faith, but it is up to the client to verify the suitability for his own particular purpose. POLYESLINE S.L. suggests to the customer to confirm these values and the compatibility of the product before use. POLYESLINE S.L. does not offer any guarantee or accept any responsibility for the suitability of the product for a particular use. For this reason, POLYESLINE S.L. will only be liable in the event that the material is defective, and only after its manufacturer confirms and ratifies it; and will never be responsible for the damages caused by its use, nor will it be responsible for them, nor for cost of the transport for return or replacement, if applicable.